

CP1131 Cascophen Kit

2 Part resorcinol adhesives such as Cascophen are accepted for use by the FAA and widely employed for structural repairs to wooden aircraft. Cascophen (also known as G1131) cures at room temperature to provide a strong, durable and waterproof joint. Resistant to most acids and organic solvents, oils and grease. Joints may be double or single spread, using a paint roller or trowel. Glue coverage 55-70 lbs per 1000 SF. Mixture ratio: 5 parts A to 1 part B by weight. Minimum use temperature 70 degrees F. Useful working life @ 70F - 3-1/4 hours. Clamp time @ 70F - 8 hours. Full cure in 6 days. Meets MIL-A-22397-1 and MIL-A-46051. For use on Wood.